

Description A medium textured slate produced from the greyest beds of the unfading grey/green deposits. Shades of grey predominate, but subtle green undertones and/or dark markings may be present.

Origin Vermont

| Lengths (inches) | Widths (inches) | Exposure (3" Headlap, inches) |
|------------------|---------------------|-------------------------------|
| 24 | 12, 14 | 10.5 |
| 22 | 11, 12, 14 | 9.5 |
| 20 | 10, 11, 12 | 8.5 |
| 18 | 9, 10, 11, 12 | 7.5 |
| 16 | 8, 9, 10, 11, 12 | 6.5 |
| 14 | 7, 8, 9, 10, 11, 12 | 5.5 |
| 12 | 6, 7, 8, 9, 10, 12 | 4.5 |

| Thickness (inches) | Pounds per Square |
|-----------------------|-------------------|
| Nominal $1/4$ - $3/8$ | 850-950 |
| $3/8$ - $1/2$ | 1,300-1,400 |
| $1/2$ - $3/4$ | 1,800-2,100 |
| $3/4$ -1 | 2,700-3,000 |
| 1 - $1 1/4$ | 3,600-4,000 |

Please note that not all sizes are available in every thickness. Call for availability.

Slate General Properties

- 100% natural product
- Exceptionally durable, 100-year useful life
- Proven historic performance & beauty
- Non-combustible—Class A Fire Resistant
- Resistant to acid rain, ultra-violet light & chemicals
- Withstands freeze/thaw cycles & high temperatures
- Rated Class 3 and Class 4 Hail Impact Resistance ($3/4$ to 2 inch ice balls)

| | This Slate* | ASTM Standards |
|--------------------|-------------|--------------------|
| Breaking Load | 798 pounds | 575 pounds minimum |
| Water Absorption | 0.205% | 0.25% maximum |
| Depth of Softening | 0.0003" | 0.002" maximum |
| ASTM Rating | S1 | |

**As tested by ASTM. Test report available upon request.*

363 Vermont 30 South, Poultney, VT 05764

802-287-2295 | Fax 802-287-2296 | newenglandslate.com | Formed by Nature, Crafted by Hand